
Composition:	Cr = 13.0 Fe = 4.2 Si = 4.5 C = 0.03 B = 2.8 Co = 1.0 Ni = Balance
--------------	--

Physical Attributes:	Solidus: 965 C / 1769 F Liquidus: 1103 C / 2017 F Braze Temp: 1135 C / 2075 F Density: 0.283 Lb. Per Cu. Inch
----------------------	--

Potential Atmospheres:	Vacuum, Inert Gases, Pure Nitrogen, Hydrogen
------------------------	--

Base Metals:	Low Carbon Steel, Stainless, Nickel, Iron Based Steels
--------------	--

Joint Performance:	Filler metal with high chromium content provides corrosion and oxidation resistance. Good strength at elevated temperatures.
--------------------	--

Potential Applications:	Jet Engine Parts, Turbine Blades, Auto EGR's Thickness: .001" up to 4.00" Wide
-------------------------	---

Size Availability:	.0015" up to 4.00" Wide .002" up to 2.00" Wide
--------------------	---

Specifications:	PWA 996 CPW 494 EMS 54752-XIII MSRR 9500-705 M3876
-----------------	--

Contact Information:

USA

Metglas[®], Inc.
440 Allied Drive
Conway, SC 29526
Tel: (800) 581-7654
Tel: (843) 349-7363
Fax: (843) 349-6815

EUROPE

Hitachi Metals Europe
Immerman Strasse 14-16
D-40210 Duesseldorf, Germany
Tel: +49 211 160 09 - 11
Fax: +49 211 160 09 - 30

ASIA

Hitachi Metals Hong Kong
Room 1107, West Wing,
Tsim Sha Tsui Centre,
66 Mody Road, TST East,
Hong Kong.
Tel: (852) 27227680
Fax: (852) 27227660

email: metglas@metglas.com
