

High Performance Brazing Filler Metal

www.metglas.com

MBF62, MBF64 and MBF67


As the world's leading producer of Amorphous Brazing Filler Metals, Metglas, Inc. continues to expand brazing alloy compositions suitable for the most demanding applications. Our newest, 100% metallic, ductile foils, MBF62, MBF64 and MBF67, offer high strength, superior corrosion resistance, quick processing, and low melting temperatures. Additionally, all Metglas Brazing Foils (MBF's) are now available in optional flangeless packaging.


New MBF62, MBF64 and MBF67 Alloy Composition

Amorphous Metals	Nominal Composition, wt %							Temperature °C (°F)		Mass Density
Designation	Ni	Cr	Fe	Si	В	Р	Mo	Solidus	Liquidus	g/cm ³
MBF62	Bal	21	< 1	0.5	0.5	8.0	1.0	878 (1612)	940 (1724)	7.74
MBF64	Bal	17.5	4.0	3.0	0.8	5.0	1.0	913 (1675)	978 (1792)	7.68
MBF67	Bal	25	< 1	1.5	0.5	6.0	1.5	890 (1634)	970 (1778)	7.70

Available Geometry

Maximum Width by Thickness								
Amorphous	Standard Foil Thickness							
Metals Designation	0.0010" (25.4 μm)	0.0015" (38.1 µm)	0.0020" (50.8 μm)					
MBF62	6.7" (170.18 mm)	8.5" (215.9 mm)	4.0" (101.6 mm)					
MBF64	6.7" (170.18 mm)	8.5" (215.9 mm)	-					
MBF67* *Tentative	6.7" (170.18 mm)	8.5" (215.9 mm)	-					





Metglas Brazing Foils offer excellent wetting and flow to fill all voids in the large number of joints in a typical plate fin heat exchanger.



Metglas® Brazing Foil Outperforms Alternative Filler Metals

Ref: MBFPL10_15_2015



High Performance Brazing Filler Metal

MBF62, MBF64 and MBF67


MAIN APPLICATIONS

1) HEAT RECYCLER

Waste heat recovery systems are gaining popularity because of rising energy costs. This finned tube heat exchanger recovers waste heat as steam for a Rankine cycle turbine.

Brazing Application

Fins must be brazed up to 30m of indivisible lengths to the tube. Approximately 22 km of tubing may be used in a single exchanger. High flexibility and the ability to resist tension and crushing during assembly are crucial. High strength, corrosion resistant joints with a uniform thickness are essential. Brazing filler metals in powder and powder-binder composites are poor candidates because of contaminating residues and possible joint shrinkage.



Tube is wrapped with MBF and fin stock in an automated brazing process


<u>Solution</u>

MBF offer the advantage of a completely automated process, purity and consistent thickness. Each tube is rotated to wrap it with foil and fin. The machine tensions brazing foil and fin stock as it turns the tube. The fins are crimped at one edge which is pressed tightly against the brazing foil. The assembly is moving continuously through an induction heating station under the cover of pure Nitrogen. Brazing occurs when the assembly passes through the high powered heating zone at 1065°C for 1–2 minutes. Easy automation and low manufacturing costs are provided.

2) PLATE-FIN HEAT EXCHANGERS

Brazing Application

High efficiency use in demanding installations where light weight, corrosion resistant and high performance are necessary, such as aerospace and automotive exhaust applications.



Metglas Brazing Foils offer excellent wetting and flow to fill all voids in the large number of joints in a typical plate fin heat exchanger.

Solution

MBF foil thickness can be controlled to provide at least 15% weight savings over similar powder alloys. Without binders or adhesives, the MBF joint is typically stronger than comparable powder, paste or tape joints by insuring clean, consistent, non-porous and complete joint coverage.


3) PLATE-PLATE HEAT EXCHANGERS

Brazing Application

The ability to resist corrosion in deionized water, ammonia, and other harsh chemical systems while sustaining design pressures up to 1760 psi (120 bar).

Solution

MBF series alloys are corrosion resistant to ammonia and other corrosive environments. High resistance to sulfuric, phosphoric, and nitric acids make MBF foil an ideal brazing filler metal for austenitic stainless steels.



Contact Information

Americas

Metglas Inc.

440 Allied Drive Conway, SC 29526

Tel: (800) 581-7654 Fax: (843) 349-6815 metglas@metglas.com